



**NOTES:**

1. IF COLDMILL OR SAWCUT IS WITHIN 24" OF EDGE OF PLANTMIX PAVING, REMOVE EXISTING PAVEMENT TO THAT EDGE AND REPLACE ENTIRE SECTION.
2. USE AC-20 ASPHALT CEMENT IN ALL LIFTS OF TYPE 2 PLANTMIX BITUMINOUS SURFACES.
3. APPLY A SEAL COAT USING SS-1 EMULSIFIED ASPHALT (MIXED WITH AN EQUAL AMOUNT OF WATER). APPLY AT A RATE OF 0.10 GPSY AND APPLY SAND BLOTTER AS NECESSARY.
4. FOR MULTIPLE PLANTMIX BITUMINOUS COURSES, TACK COAT SHALL BE APPLIED BETWEEN EACH PLANTMIX BITUMINOUS COURSE.

NO.	REVISION	DATE	STANDARD DETAILS FOR PUBLIC WORKS CONSTRUCTION		SECTION
			PAVEMENT PATCH		ROADWAY
					DRAWING NO.
			CITY OF ELKO, NEVADA		R-9.1
					DATE
					11/30/07
					PAGE
					1